

IN THE SPECIFICATION:

On page 10, please amend columns 9 and 10 of Table II as follows:

Table II

Hemp Hurd Fiber	Resin Content (wt. %)	OOP Caliper (inches)	OOP Specific Gravity	24-hour Water Gain (%)	24-hour Caliper Swell (%)	Internal Bond Strength (psi)	Cleavage (lbs)	Smoothness Value (Fine Coarse)	Smoothness Value (Course Fine)
Fine	3	0.124	1.05	28.4	18.8	186.4	58.5	2.1	3.1
Coarse	3	0.127	1.03	28.7	19.2	140.2	47.6	2.4	3.7
Fine	5	0.123	1.05	26.7	15.8	247.1	64.8	2.3	3.8
Coarse	5	0.126	1.03	24	14.5	187.2	53.5	2.4	3.8